



TECHNICAL DATA SHEET - RCABC

STOCK NO. 0670088

JULY, 2016

No. 15 PERFORATED ASPHALT

SATURATED FELT - IMPERIAL

This product consists of a resilient, high-strength cellulose fiber mat that has been saturated with premium waterproofing bitumen. Used as a vapour retarder on certain substrates or as a membrane for multi-ply built-up roofing systems, IKO's No. 15 Perforated Asphalt Saturated Felt Imperial meets or exceeds ASTM D226 Type I and CSA A123.3 Type 1 compositional and performance characteristics. IKO's products are produced and designed with consideration for environmental responsibility and sustainability, incorporating quality recycled components whenever possible, manufactured in facilities that comply with the most stringent government environmental regulations, and can therefore be a part of any "green" construction project.

CHARACTERISTIC	UNITS	NOMINAL VALUE	TEST METHOD	STANDARD LIMITS
QUANTITY PER PALLET:	-	25	-	N/A
PALLET SIZE:	cm (in)	107 x 107 (42 x 42)	-	-
LENGTH:	m (ft)	43.9 (144)	-	± 0.1%
WIDTH:	mm (in)	914 (36)	-	± 3 (1/8)
WEIGHT:	kgs (lbs)	22.7 (50)	-	-
AREA:	m ² (ft ²)	40 (432)	-	-
LINES:	mm (in)	51 (2) 216 (8 1/2) 286 (11 1/4) 432 (17)	-	± 6 (1/4)
SATURATION:	%	125	ASTM D228	MIN: 120
TENSILE STRENGTH	MD: XD:	kN/m (lbf/in) kN/m (lbf/in)	7.1 (41) 3.6 (21)	ASTM D146 MIN: 5.25 (30) MIN: 2.63 (15)

The information on this Technical Data sheet is based upon data considered to be true and accurate, based on laboratory tests and production measurements, and is offered solely for the user's consideration, investigation and verification. Nothing contained herein is representative of a warranty or guarantee for which the manufacturer can be held legally responsible. The manufacturer does not assume any responsibility for any misrepresentation or assumptions the reader may formulate.