

POLYSTICK® IR-Xe

SELF-ADHERED ICE AND WATER PROTECTION UNDERLAYMENT

PRODUCT DESCRIPTION

Polystick IR-Xe, is a homogeneous rubberized asphalt waterproofing compound, fiberglass reinforced, with an aggregate surface for skid resistance for use in ice and water protection applications. The rubberized asphalt seals around correctly installed nails on the weathering surface. Split release backing film aids in easy positioning of sheets to maintain proper line.

Polystick IR-Xe underlayments are manufactured using patented ADESO® dual compound Self-Adhesive technology, whereby a “true” polymer modified asphalt compound is applied on the top layer and an aggressive self-adhesive compound is applied on the bottom layer.

TYPICAL APPLICATIONS

- Specially designed for multiple steep slope applications
- Designed as effective reinforcement for perimeter and flashing details
- Added protection against areas prone to wind driven rain and ice damming

FEATURES AND BENEFITS

- Proprietary asphalt compound and fiberglass mat for exceptional dimensional stability
- Surface engineered for superior slip resistance and long-term performance
- Aggressive self-adhesive compound for ease of application

TECHNICAL DESCRIPTION*

TEST METHOD	PROPERTY	ASTM VALUE
ASTM D5147	Maximum Load, Longitudinal and Transverse, min, kN/m (lbf/in.)	4.4 (25)
ASTM D5147	Elongation at break, min of modified bitumen portion (%)	10
ASTM D5147	Tear Resistance, Longitudinal and Transverse, min, N (lbf)	89 (20)
ASTM E96	Moisture Vapor Permeability, max, perms	0.1
ASTM D1970	Adhesion to Plywood min at 40°F, lbf/ft width	2.0
ASTM D1970	Adhesion to Plywood min at 75°F, lbf/ft width	12.0
ASTM D1970	Sealability around nail	pass
ASTM D1970	Waterproof integrity after low temp flexibility	pass
ASTM D1970	Waterproof integrity of lap seam	pass
ASTM D1970	Slip Resistance	pass

*The properties in this table are "as manufactured" unless otherwise noted



PRODUCT DATA**

Approx Coverage (Nominal)2 squares
 Weight (Approx) - SAND 61 lbs
 Weight (Approx) - MINERAL 56 lbs
 Thickness (Nominal) 1.5 mm; 60 mils
 Roll Size65' x 36"
 Rolls/Pallet - BOX20
 Rolls/Pallet - SHRINK WRAP30

PRODUCT DATA**

Approx Coverage (Nominal) 1 square
 Weight (Approx) - SAND 33 lbs
 Weight (Approx) - MINERAL 31 lbs
 Thickness (Nominal) 1.5 mm; 60 mils
 Roll Size33.4' x 36"
 Rolls/Pallet - SHRINK WRAP48
 ** All values are nominal at time of manufacturing

APPLICABLE STANDARDS

- ASTM D1970
- UL Classified for use in class A, B or C roofs, as listed in the latest UL “Roofing Materials and Systems Directory”
- ICC ESR-1697
- Florida Building Code Approved
- Miami Dade Code Compliance



www.polyglass.us

POLYSTICK® IR-Xe

SELF-ADHERED ICE AND WATER PROTECTION UNDERLAYMENT

APPLICATION INSTRUCTIONS

- Apply Polystick IR-Xe directly to the roof deck.
- Do not apply to shingles or other roof coverings.
- Apply only when the weather is dry and material interface temperatures (air, roof deck, membrane) are 40°F and rising.
- Always start at the lowest point of the roof deck where possible.
- Cut the Polystick IR-Xe to a suitable, workable length prior to placement.
- Lay the material flat in place, starting at the lowest point.
- Overlap seams 3" minimum and endlaps 6" minimum.
- Peel half of the backing off the roll and apply firm, even pressure from the center to the outer edges.
- Remove the backing from the remaining half of the roll and apply pressure.
- Always ensure that Polystick IR-Xe is applied over the area to cover the highest point of "ice damming".
- Be sure to follow all local building code recommendations and requirements with regards to the width of ice dam materials.
- If full roof coverage application is desired, proper venting of the structure is recommended. Consult a design professional for proper venting requirements. Applications involving non-ventilated attics or sheathing with radiant barriers, an anchor sheet is recommended to allow venting and prevent the creation of a double vapor barrier condition.
- In steep slope applications (i.e. 2:12 slope or higher) where backnailing will be required, be sure that all nails are covered by the overlapping next sheet.
- Manufacturer recommends applying covering within 90 days unless otherwise limited by the Authority Having Jurisdiction(AHJ).

POLYGLASS U.S.A., INC. MANUFACTURING FACILITIES

- Fernley, NV
- Hazleton, PA
- Waco, TX
- Winter Haven, FL
- Ponte di Piave, Italy

CORPORATE HEADQUARTERS

Polyglass U.S.A., Inc.
1111 West Newport Center Drive
Deerfield Beach, FL 33442
www.polyglass.us

General Line: (888) 410-1375
(954) 233-1330

Customer Service: (800) 222-9782

Technical Service: (866) 802-8017

Questions? technical@polyglass.com

Product Disclaimer: Unless otherwise incorporated into or part of a supplemental manufacturer's warranty, Polyglass warrants its product(s) against manufacturing defects in its product that directly results in leakage for a period of 1 year.

Refer to safety data sheet (SDS) for specific data and handling of our products. All data furnished refers to standard production and is given in good faith within the applicable manufacturing and testing tolerances.

Polyglass U.S.A., Inc., reserves the right to improve and change its products at any time without prior notice. Polyglass U.S.A., Inc. cannot be held responsible for the use of its products under conditions beyond its own control.

For most current product data and warranty information, visit www.polyglass.us

Copyright ©2017 by Polyglass U.S.A., Inc and all rights are reserved

Edition Date: 07/17 • Doc# Polystick IR-Xe



www.polyglass.us