

# SYNTRACK

PRO BUILDER ROOFING UNDERLAYMENT

## TECHNICAL DATA SHEET

### SynTrack: TECHNICAL DATA SHEET

Specification & Standard	Syn Track	#15 Felt
Length / width per roll	48" x 250ft	36" x 144 ft
Weight / sq. ft. per roll	20 lbs (9 kg) / 1000 sq.ft.	45lbs / 432 sq.ft.
Rolls per pallet (44" x 44")	64	25
Rolls per truckload - 32 pallets	2048	1000
Rolls required per 1,000 Sq feet	1	2.5
100% recyclable	Yes	No
Material composition	Polyolefin	Asphalt
UV resistance	90 days	None
Breaking strength ASTM D 5034 MD / CD	85 lb (38.6 kg) / 80 lb (36.3 kg)	NA
Tear strength ASTM D4533 MD / CD	23 lb (10 kg) / 21 lb (9.52 kg)	NA
Water shower exposure ASTM D 4869	Pass	NA
Permeability ASTM E96	<0.05 Perms	6 Perms
Mullen Burst	100 psi	NA
Nominal thickness ASTM D1777	8 mils	21 mils
Temperature range	-40° F to 240° F	
Enhanced slip resistant surface	Excellent	Basic
Limited warranty	15 years	None

The data shown above is based on the test averages and independent test reports. There can be a +/-10% variation in the individual test results. This report should not be considered as a warranty for the manufacturer. The manufacturer is not responsible for the misrepresentation or misinterpretation of the data by the reader. Please find out more about the product by calling 1-844-353-9839 or visit [www.ftsyn.com](http://www.ftsyn.com). The SynTrack logo is a registered trademark of FT Synthetics Inc.