

# SOPRAFLASH FLAM STICK

TECHNICAL DATA SHEET 240214SCANE

(supersedes 230927SCANE)



WATERPROOFING

APPLICATIONS

ROOFS

## DESCRIPTION

SOPRAFLASH FLAM STICK is a base sheet membrane composed of SBS modified bitumen and a glass mat reinforcement. The surface is covered with a thermofusible plastic film and the self-adhesive underface is covered with a silicone release film.

## SURFACE PREPARATION

Surfaces must be clean, dry and free of loose particles. The membrane is installed over the substrate previously primed with one of the ELASTOCOL STICK primers.

## INSTALLATION

### SELF-ADHESIVE

SOPRAFLASH FLAM STICK is adhered to the substrate by peeling off the release silicone release film.

Once the membrane is in place, apply pressure over the whole surface using a membrane roller to ensure a complete and uniform adhesion.

When completing the end lap, burn the plastic film over the last 150 mm (6 in) of the membrane before installing the next membrane. Finish the application by welding the last 25 mm (1 in) of the side lap using a propane torch and a membrane roller.

Minimum application temperature summer grade: 10 °C (50 °F)

Minimum application temperature winter grade: -10 °C (14 °F)

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

## GENERAL INFORMATION

Specifications	SOPRAFLASH FLAM STICK
Reinforcement	Glass mat
Dimensions	15 x 1 m (49 x 3.3 ft)
Selvedge width	75 mm (3 in)
Surface	Thermofusible plastic film
Underface	Self-adhesive, covered with a silicone release film

(All values are nominal)



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE: All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.

# SOPRAFLASH FLAM STICK

TECHNICAL DATA SHEET 240214SCANE

(supersedes 230927SCANE)



WATERPROOFING

APPLICATIONS

ROOFS

## PROPERTIES

Properties	SOPRAFLASH FLAM STICK		CSA A123.23 Type A, Grade 3 Requirements
	BEFORE Heat Conditioning	AFTER Heat Conditioning	
Thickness, min.	2.5 mm (98 mils)		2.0 mm (80 mils)
Selvage thickness, min.	2.5 mm (98 mils)		2.0 mm (80 mils)
Mass per unit area, min.	3.0 kg/m <sup>2</sup> (60 lb/100 ft <sup>2</sup> )		2.2 kg/m <sup>2</sup> (45 lb/100 ft <sup>2</sup> )
Strain energy, min. MD/XD, at 23 °C ± 2 °C (73.4 °F ± 3.6 °F) at -18 °C ± 2 °C (0 °F ± 3.6 °F)	1/1 kN/m (5.7/5.7 lbf/in) 0.5/0.5 kN/m (2.8/2.8 lbf/in)	2.1/0.5 kN/m (12/2.8 lbf/in) 0.5/0.4 kN/m (2.8/2.3 lbf/in)	Report value Report value
Peak load, min. MD/XD, at 23 °C ± 2 °C (73.4 °F ± 3.6 °F) at -18 °C ± 2 °C (0 °F ± 3.6 °F)	12/13.5 kN/m (69/77 lbf/in) 23/21 kN/m (131/120 lbf/in)	18/16 kN/m (103/91 lbf/in) 21/21 kN/m (120/120 lbf/in)	5.3 kN/m (30 lbf/in) 12.3 kN/m (70 lbf/in)
Elongation at peak load, min. MD/XD, at 23 °C ± 2 °C (73.4 °F ± 3.6 °F) at -18 °C ± 2 °C (0 °F ± 3.6 °F)	6/7% 4/4%	8/5% 3/4%	2/2% 1/1%
Ultimate elongation, MD/XD, at 23 °C ± 2 °C (73.4 °F ± 3.6 °F)	35/30%	10/7%	3/3%
Dimensional stability, max. MD/XD	±0.3/±0.1%		0.5%
Low temperature flexibility, max. MD/XD	-30/-30 °C (-22/-22 °F)	-18/-18 °C (-0.4/-0.4 °F)	-18 °C (-0.4 °F)
Compound stability	91/91 °C (195/195 °F)		min. 91 °C (195 °F)

(All values are nominal)

## STORAGE AND HANDLING

Rolls must be stored upright, with the selvage side on top. If the products are stored outdoors, cover them with an opaque protection cover after removal of the delivery packaging.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE : All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.

sopca-en-ca-tds-sopraflash-flam-stick.indd