

## JM EPDM NR 45 MIL

## Ethylene Propylene Diene Monomer Membrane

#### Meets the requirements of ASTM D 4637, Type I

#### **Features and Components**

Membrane: Nonreinforced, cured EPDM (ethylene propylene diene monomer).


Fully Extruded: Produces fewer air voids, more uniform thickness and smoother sheets.

Vulcanization Process: Combines two layers of membrane to produce a fully cross-linked monolithic membrane.

Membrane Formulation: Performs in extreme temperature climates and withstands differential movement (elongation).

UV-Stabilization Properties: Offers outstanding ozone and weather resistance delivering one of the longest service lives available.

Technical Expertise: Backed by 30+ years of EPDM experience and installations.



Component Membrane

Single Ply

Color

Black

#### System Compatibility This product may be used as a component in the following systems. Please reference product application for specific installation methods and information.

Ē	ПА	UA	Do not i	use with l	Multi-Ply	systems	ПАА	3A		Sing	IV
盂	ЦΛ	CA	CA	LIVA	ЦΛ	CA	LIVA/	C A		<u>e</u>	B/
<u>~</u>	BU		Al	PP	SBS					픋	

á		DUN APP				303			一		IFU	FVG		EPDINI		
Ŧ	Н	A CA	CA	HW	HA	CA	HW	SA	gle	MF	FA	MF	FA	MF	FA	BA
Ž			Do not	use with I	Multi-Ply	systems			Si		Compatible	with the se	lected Sir	igle Ply syste	ms abov	е
Ke	y: H	A = Hot Applie	d CA =	Cold Ap	plied <b>H</b>	<b>W</b> = Heat	t Weldable	SA =	Self Adhe	red MF	F = Mechani	cally Fasten	ed <b>FA</b> =	Fully Adhere	d <b>BA</b> :	= Ballasted

#### **Energy and the Environment**

Property	Value		
Reflectivity* (ASTM C 1549)	0.06		
Emissivity* (ASTM C 1371)	0.88		
Post-consumer Recycled Content	0%		
Pre-Consumer Recycled Content	0%		

<sup>\*</sup>Test methods for reflectivity and emissivity are LEED®- and CRRC®-approved.

#### **Peak Advantage® Guarantee Information**

Enhanced guarantees are now available on certain systems for wind and puncture. Consult your local sales representative for more information and for specific guarantee terms and costs

Product	Guarantee Term
When used in most JM EPDM Systems*	Up to 15 years

<sup>\*</sup>Contact JM Technical Services for specific systems.

#### Codes and Approvals





#### Installation/Application





Refer to JM EPDM Application Guides and Detail Drawings for instructions.

#### **Packaging and Dimensions**

Roll Size	Roll Coverage
10' x 50' (3.05 m x 15.24 m)	500 ft <sup>2</sup> (46.45 m <sup>2</sup> )
10' x 100' (3.05 m x 30.48 m)	1000 ft <sup>2</sup> (92.9 m <sup>2</sup> )
20' x 50' (6.1 m x 15.24 m)	1000 ft <sup>2</sup> (92.9 m <sup>2</sup> )
20' x 100' (6.1 m x 30.48 m)	2000 ft² (185.8 m²)
30' x 100' (9.14 m x 30.48 m)	3000 ft <sup>2</sup> (278.71 m <sup>2</sup> )
40' x 100' (12.19 m x 30.48 m)	4000 ft² (371.6 m²)
Extruded in:	Milan, OH

<sup>\*</sup>Assumes 48' flatbed truck



# JM EPDM NR 45 MIL

Ethylene Propylene Diene Monomer Membrane

## Meets the requirements of ASTM D 4637, Type I

### **Tested Physical Properties**

Physic	al Properties	ASTM Test Method	Standard for ASTM D 4637, Type I	JM EPDM – NR 45 mil	
	Tensile Strength (psi)	D 412	>= 1305	1686	
	Elongation, Ultimate (%)	D 412	>= 300	451	
Strength	Tensile Set (%)	D 412	<=10	0.4	
Stre	Tear Resistance (lbf/in.)	D 624	> = 150	185	
	Dynamic Puncture Resistance, 5J, Type I	D 5635	pass	pass	
	Static Puncture Resistance, 44.1 lbf, Type I	D 5602	pass	pass	
	Overall Sheet Thickness (in.)	D 751	+/- 10%	pass	
evity	Brittleness Point (°F)	D 2137	<= -49	pass	
Longevity	Ozone Resistance	D 1149	pass	pass	
	Water Absorption (mass %)	D 471	<=8	0.55	
	Heat Aged 670 hrs @ 240°F	D 573			
led ince	Tensile Strength (psi)	D 412	> = 1205	1693	
Heat Aged Performance	Elongation, Ultimate (%)	D 412	> = 200	287	
Perf	Tear Resistance (lbf/in.)	D 624	> = 125	149	
	Linear Dimensional Change (%)	D 1204	< +/- 1	0.4	
ring	Weathering Resistance, 5040 KJ/(m2-nm) @ 340 nm	D 4637 / G 151 / G 155			
Weathering Performance	Visual Inspection	_	pass	pass	
We	Elongation, Ultimate (%)	D 412	> = 200	449	