

ELASTOPHENE 180 SANDED



WATERPROOFING

APPLICATIONS

ROOFS

TECHNICAL DATA SHEET 240403SCANE

(supersedes 230927SCANE)

DESCRIPTION

ELASTOPHENE 180 SANDED is a base sheet membrane composed of SBS modified bitumen and a non-woven polyester reinforcement. Both sides are sanded.

INSTALLATION

HOT BITUMEN

ELASTOPHENE 180 SANDED is unrolled in a bed of hot bitumen (SEBS or oxidized) applied with a mop.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

GENERAL INFORMATION

Specifications	ELASTOPHENE 180 SANDED
Reinforcement	Non-woven polyester
Dimensions	15 x 1 m (49 x 3.3 ft)
Selvage width	75 mm (3 in)
Surface	Sanded
Underface	Sanded

(All values are nominal)



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE: All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.



WATERPROOFING

APPLICATIONS

ROOFS

ELASTOPHENE

180 SANDED

TECHNICAL DATA SHEET 240403SCANE

(supersedes 230927SCANE)

PROPERTIES

Properties	ELASTOPHENE 180 SANDED		CSA A123.23 Type B, Grade 3 Requirements
	BEFORE Heat Conditioning	AFTER Heat Conditioning	
Thickness, min.	2.2 mm (85 mils)		2.2 mm (85 mils)
Selvage thickness, min.	2.2 mm (85 mils)		2.2 mm (85 mils)
Mass per unit area, min.	2.6 kg/m ² (53 lb/100 ft ²)		2.6 kg/m ² (53 lb/100 ft ²)
Strain energy, min. MD/XD, at 23 °C ± 2 °C (73.4 °F ± 3.6 °F) at -18 °C ± 2 °C (0 °F ± 3.6 °F)	6.5/6.5 kN/m (37/37 lbf/in) 8.0/4.0 kN/m (46/23 lbf/in)	5.5/5.5 kN/m (31/31 lbf/in) 3.1/3.1 kN/m (18/18 lbf/in)	5.5 kN/m (31 lbf/in) 3.0 kN/m (17 lbf/in)
Peak load, min. MD/XD, at 23 °C ± 2 °C (73.4 °F ± 3.6 °F) at -18 °C ± 2 °C (0 °F ± 3.6 °F)	15/11 kN/m (86/63 lbf/in) 22/17 kN/m (126/97 lbf/in)	14/10 kN/m (80/57 lbf/in) 19/11 kN/m (108/63 lbf/in)	Report value Report value
Elongation at peak load, min. MD/XD, at 23 °C ± 2 °C (73.4 °F ± 3.6 °F) at -18 °C ± 2 °C (0 °F ± 3.6 °F)	50/60% 30/30%	15/50% 7/21%	Report value Report value
Ultimate elongation, MD/XD, at 23 °C ± 2 °C (73.4 °F ± 3.6 °F)	55/70%	45/45%	Report value
Dimensional stability, max. MD/XD	±0.5/±0.1%		1.0%
Low temperature flexibility, max. MD/XD	-18/-18 °C (-0.4/-0.4 °F)	-18/-18 °C (-0.4/-0.4 °F)	-18 °C (-0.4 °F)
Compound stability	121/121 °C (250/250 °F)		min. 102 °C (215 °F)
Resistance to puncture	Pass		Pass
Water vapour transmission, as per ASTM E96 (Procedure B)	< 2.5 ng/Pa•s•m ² (< 0.04 perm)		N/A

(All values are nominal)

STORAGE AND HANDLING

Rolls must be stored upright, with the selvage side on top. If the products are stored outdoors, cover them with an opaque protection cover after removal of the delivery packaging.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE : All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.

sopca-en-ca-tds-elastophene-180-sable.indd